

SODIUM ALUMINOSILICATE

Prepared at the 17th JECFA (1973), published in FNP 4 (1978) and in FNP 52 (1992). Metals and arsenic specifications revised at the 57th JECFA (2001). An ADI 'not specified' for silicon dioxide and certain silicates, was established at the 29th JECFA (1985)

SYNONYMS	Sodium silicoaluminate; INS No. 554
DEFINITION	A series of hydrated sodium aluminium silicates. The article of commerce may be specified further as to silicon dioxide, aluminium oxide, and sodium oxide content, loss on drying, loss on ignition and pH of a slurry in water.
Chemical names	Sodium aluminosilicate
DESCRIPTION	Odourless, fine, white amorphous powder, or as beads.

FUNCTIONAL USES

Anticaking agent

CHARACTERISTICS

IDENTIFICATION

<u>Solubility</u> (Vol. 4)	Insoluble in water and ethanol, partially soluble in strong acids and alkali hydroxides
<u>Test for sodium</u> (Vol. 4)	Passes test
<u>Test for aluminium</u> (Vol. 4)	Passes test
<u>Test for silicate</u>	Passes test See description under TESTS

PURITY

<u>Lead</u> (Vol. 4)	Not more than 5 mg/kg Determine using an atomic absorption technique appropriate to the specified level. The selection of sample size and method of sample preparation may be based on the principles of the method described in Volume 4, "Instrumental Methods."
----------------------	---

TESTS

IDENTIFICATION TESTS

<u>Test for silicate</u>	Mix about 500 mg of the sample with about 200 mg of anhydrous sodium carbonate and 2 g of anhydrous potassium carbonate, and heat the mixture in a platinum or nickel crucible until it melts completely. Cool, add 5 ml of water, and allow to stand for 3 min. Heat the bottom of the crucible gently, detach the melt, and transfer it to a beaker with the aid of about 50 ml of water. Add gradually hydrochloric acid until no effervescence is observed, then add 10 ml more of the acid, and evaporate the mixture on a steam bath
--------------------------	--

to dryness. Cool, add 20 ml of water, boil and filter the mixture through an ash-free filter paper. An insoluble residue of silica remains. (Note. Retain the filtrate for the test for aluminium). Transfer the gelatinous residue into a platinum dish, and cautiously add 5 ml of hydrofluoric acid (warning: toxic, corrosive, must not contact skin; work under fume hood). The precipitate dissolves. (If it does not dissolve, repeat the evaporation with hydrofluoric acid.) Heat and hold in the vapours a glass stirring rod with a drop of water on the tip. The drop becomes turbid.